

Appl. No. : 09/995,816  
Filed : November 27, 2001

#### LISTING OF THE PENDING CLAIMS

1. (Previously presented) An electroluminescent device comprising at least one of a hole-injecting layer and an electron-injecting layer, wherein the at least one of the hole-injecting layer and the electron-injecting layer comprises a polymeric compound and a movable ion, wherein the polymeric compound has at least one block of  $[O-(CH_2)_x]_y$  units and at least one non-movable ionic moiety, wherein x is an integer equal to or greater than two, wherein y is an integer equal to or greater than two, and wherein the movable ion and the at least one non-movable ionic moiety are counter ions.
2. (Previously presented) An electroluminescent device comprising:
  - a substrate;
  - a first electrode deposited on the substrate;
  - an emissive layer comprising an organic electroluminescent material;
  - a second electrode deposited over the electron-injecting layer;
  - at least one of a hole-injecting layer and an electron injecting layer, the hole-injecting layer being positioned between the emissive layer and the first electrode, the electron-injecting layer being positioned between the emissive layer and the second electrode; and
  - wherein the hole-injecting layer, the electron-injecting layer, or both, comprises a polymeric compound and a movable ion, wherein the polymeric compound has at least one block of  $[O-(CH_2)_x]_y$  units and at least one non-movable ionic moiety, wherein x is an integer equal to or greater than two, wherein y is an integer equal to or greater than two, and wherein the movable ion and the at least one non-movable ionic moiety are counter ions. (Currently amended) The electroluminescent device of Claim 2, wherein the substrate comprises a material selected from the group consisting of glass, quartz, and polyethylene terephthalate.
3. (Previously presented) The electroluminescent device of Claim 2, wherein the first electrode comprises a material selected from the group consisting of lead oxide, indium tin oxide, doped polyaniline, doped polypyrrole, doped polythiophene, and polyethylene dioxythiophene.
4. (Original) The electroluminescent device of Claim 2, wherein the emissive layer comprises a material selected from the group consisting of emissive conjugated polymer,

AppL No. : 09/995,816  
Filed : November 27, 2001

emissive non-conjugated polymer, emissive monomeric or oligomeric material, poly(meta-methylacrylic acid), poly(styrene), and poly(9-vinylcarbazole).

5. (Original) The electroluminescent device of Claim 4, wherein the emissive conjugated polymer is selected from the group consisting of poly(*p*-phenylene vinylene), poly(thiophene), poly(*p*-phenylene), poly(fluorene), poly(arylenes), poly(arylene vinylene), polyquinoline, polypyrrole, polyaniline, polyacetylene, and derivatives thereof.


6. (Original) The electroluminescent device of Claim 4, wherein the emissive non-conjugated polymer is a polymer having non-conjugated main chains and side chains substituted with emissive functional groups.

7. (Original) The electroluminescent device of Claim 4, wherein the emissive monomeric or oligomeric material is selected from the group consisting of alumina quinone, rubrene, anthracene, perylenene, coumarine 6, Nile red, aromatic diamine, N,N'-diphenyl-N,N'-bis-(3-methylphenyl)-1,1'-biphenyl-4,4'-diamine), (3-(4-biphenyl)-4-phenyl-5-(4-tert-butylphenyl)-1,2,4-triazole), (dicyanomethylene)-2-methyl-6-(*p*-dimethylaminostyryl)-4*H*-pyran), and derivatives thereof.

8. (Previously presented) The electroluminescent device of Claim 2, wherein the second electrode comprises a material selected from the group consisting of aluminum, magnesium, lithium, calcium, copper, silver, iron, platinum, indium, palladium, tungsten, zinc, gold, lead, and alloys thereof.

9. (Previously presented) The electroluminescent device of Claim 2, wherein the movable ion in the hole-injecting layer is an anion.

10. (Previously presented) The electroluminescent device of Claim 2, wherein the polymeric compound is represented by one or more formulas selected from the group consisting of the formula (III) and formula (IV),




wherein EO represents ethylene oxide; NonEO represents non-ethylene oxide; PO represents propylene oxide; NonPO represents non-propylene oxide; A\* represents an

Appl. No. : 09/995,816  
Filed : November 27, 2001

$C^+$  represents a cation;  $m + n = 1$ ; and  $n$  represents a number more than 0 and less than 1.

11. (Previously presented) The electroluminescent device of Claim 2, wherin the movable ion in the electron-injecting layer is a cation.

12. (Previously presented) The electroluminescent device of Claim 11, wherein the polymeric compound is represented by one or more formulas selected from the group consisting of the formula (I) and the formula (II),



wherein EO represents ethylene oxide; NonEO represents non-ethylene oxide; PO represents propylene oxide; NonPO represents non-propylene oxide; A<sup>-</sup> represents an anion; C<sup>+</sup> represents a cation; m + n = 1; and n is a number more than 0 less than 1.

13. (Previously presented) An electroluminescent device comprising:

a transparent substrate;

a semitransparent electrode deposited on the transparent substrate;

a hole-injecting layer positioned on the semitransparent electrode, the hole-injecting layer comprising a polymeric compound and a movable anion, the polymeric compound having at least one block of  $[O-(CH_2)_x]_y$  units and at least one non-movable cationic moiety, wherein  $x$  is an integer equal to or greater than two, wherein  $y$  is an integer equal to or greater than two;

an emissive layer comprising an organic electroluminescent material, positioned on the hole-injecting layer;

an electron-injecting layer positioned on the emissive layer, the electron-injecting layer comprising a polymeric compound and a movable cation, the polymeric compound having at least one block of  $[O-(CH_2)_x]_y$  unit; and at least one non-movable anionic moiety, wherein  $x'$  is an integer equal to or greater than two, wherein  $y'$  is an integer equal to or greater than two; and

- metal electrode deposited on the electron-injecting layer.